



## Steel grade

Material No. / Werkstoff-Nr.	PREMIUM 1.2083
Description	X40Cr14
AISI/SAE	420
Search for alternatives in the ABRAMS STEEL GUIDE®	<a href="http://www.steel-guide.eu/alternatives/420">www.steel-guide.eu/alternatives/420</a>


## Specifications



**Precision flat steel with machining allowance [PFS/BA]**  
L: 1.000 mm



**€co-Präz® [Eco]**  
L: 500 mm



**Precision round steel without machining allowance [PRS]**  
bright drawn / ground, ISO h9  
L: 1.000 mm  
**with machining allowance [PRS/BA]**  
peeled / rough-turned  
L: 500 mm  
L: 1.000 mm

## Chemical composition AISI/SAE 420 (reference value %)

C	Si	Mn	P	S	Cr
0,36 - 0,42	0 - 1,0	0 - 1,0	0 - 0,03	0 - 0,03	12,5 - 14,5

## Physical properties

Hardness (delivery condition)	max. 241 HB, annealed						
Tensile strength $R_m$ (as received condition)	approx. 815 N/mm <sup>2</sup>						
Working hardness	max. 55 HRC						
Thermal expansion coefficient $10^{-6}m/(m \cdot K)$	20 - 100°C	20 - 200°C	20 - 300°C	20 - 350°C	20 - 400°C	20 - 450°C	20 - 500°C
	11,1	11,6	12,0	12,3	12,4	12,5	12,6
Thermal conductivity $W/(m \cdot K)$	23°C	150°C	300°C	350°C	400°C	500°C	
	22,6	24,0	24,6	24,9	24,4	23,7	

## Technical properties

Corrosion-resistant cold work steel and plastic mould steel, good machinability. Can be hardened and polished. Low distortion through-hardening steel with high hardness and high wear resistance. For maximum required polishability use the ESR (Electro Slag Remelted Steel) production.

## Applications

Machine construction, medical technology, plastic moulds, synthetic resin mould tools, die casting tools, light metal die casting, cutting tools, machine knives, kitchen knives, razors, shears, scraper blades, surgical instruments, measuring tools, roller bearings, ball bearings, ice-skates, pump parts, valves.

## Heat treatment

Soft annealing	Temperature	Cooling	Hardness			
	760 - 800°C	Furnace	max. 241 HB			
Stress relief annealing	Temperature	Cooling				
	600 - 650°C	Furnace				
Hardening	Temperature	Quenching in	Hardness after quenching			
	1000 - 1050°C	Oil, basin (500 - 550°C)	56 HRC			
Tempering	100°C	200°C	300°C	400°C	500°C	600°C
	56 HRC	55 HRC	52 HRC	51 HRC	52 HRC	40 HRC

## ABRAMS PREMIUM STEEL

is a registered trademark of  
Abrams Engineering Services GmbH & Co. KG  
Hannoversche Str. 38 - 49084 Osnabrueck / Germany  
Managing Director: Dipl.-Wi.-Ing. Dr. Juergen Abrams

Amtsgericht Osnabrueck / Germany, HRA 6865  
VAT-No.: DE 221940667  
General Partner: Abrams Engineering Verwaltungs GmbH  
Amtsgericht Osnabrueck / Germany, HRB 20019

T: +49 (0) 5 41/3 57 39-0  
F: +49 (0) 5 41/3 57 39-39

sales@premium-steel.eu  
www.premium-steel.eu  
www.shop.premium-steel.eu  
www.steel-guide.eu

[www.premium-steel.eu/news](http://www.premium-steel.eu/news)



